## LISTING OF THE CLAIMS

This listing of claims will replace all prior versions, and listings, of claims in the application.

1 (currently amended): A high-strength hot-rolled steel sheet excellent in hole expandability, and ductility, containing consisting essentially of, in terms of a mass%:

C: 0.01 to 0.09%,

Si :  $0.05 \ 1.0$  to 1.5%,

Mn : 0.5 to 3.2%,

Al : 0.003 to 1.5%,

P : 0.03% or below,

S : 0.005% or below,

Ti : 0.10 to 0.25%,

Nb : 0.01 to 0.05%, and

the balance consisting of being iron and unavoidable impurities; wherein the steel of said steel sheet contains substantially no Mg and satisfying all of the following formulas <1> to <3>:

$$0.9 \le 48/12 \times C/Ti < 1.7$$
 ... <1>

$$50,227 \times C - 4,479 \times Mn > -9,860 \dots <2>$$

having strength of at least 980 N/mm<sup>2</sup>.

2 (currently amended): A high-strength hot-rolled steel sheet excellent in hole expandability and ductility, containing consisting essentially of, in terms of a mass%:

C: 0.01 to 0.09%,

Si : 0.05 1.0 to 1.5%,

Mn : 0.5 to 3.2%,

Al: 0.003 to 1.5%,

P : 0.03% or below,

S : 0.005% or below,

Ti: 0.10 to 0.25%,

Nb: 0.01 to 0.05%,

at least one of

Mo: 0.05 to 0.40% and V:0.001 to 0.10%, and

the balance consisting of being iron and unavoidable impurities;
wherein the steel of said steel sheet contains substantially no Mg and satisfying all of the following formulas <1>' to <3>':

$$0.9 \le 48/12 \times C/Ti < 1.7$$
 ... <1>'
 $50,227 \times C - 4,479 \times (Mn + 0.57 \times Mo + 1.08 \times V) >$ 
 $-9,860$  ... <2>'
 $811 \times C + 135 \times (Mn + 0.57 \times Mo + 1.08 \times V) + 602 \times Ti + 794 \times Nb >$ 
 $465$  ... <3> <3>', and

having strength of at least 980 N/mm<sup>2</sup>.

3 (previously presented): A high-strength hot-rolled steel sheet excellent in hole expandability and ductility according to claim 1 which further contains, in terms of mass%, 0.0005 to 0.01% of at least one of Ca, Zr and REM.

4 (canceled).

5 (currently amended): A high-strength hot-rolled steel sheet excellent in hole expandability and ductility according to claim 1 any of claims 1 to 3, which further contains, in terms of mass%, at least one of:

Cu

0.1 to 1.5% and

Ni

0.1 to 1.0%.

6 (withdrawn): A production method of a high strength hot rolled steel sheet excellent in hole expandability and ductility according to claim 1, comprising the steps of:

finishing hot rolling by setting a rolling end temperature to from an Ar<sub>3</sub> transformation point to 950°C;

cooling a hot rolled steel sheet to 650 to 800°C at a cooling rate of at

least 20°C/sec;

air cooling then the steel sheet for 0.5 to 15 seconds;

further cooling the steel sheet to 300 to 600°C at a cooling rate of at

least 20°C/sec; and

coiling the steel sheet.